

FIBERWEB

DATA SHEET

BOND-N-FLASH MASTIC

Description: **BOND-N-FLASH Mastic** is an all weather butyl mastic specifically formulated to permanently seal all laps, seams and terminations in the application of **BOND-N-FLASH** stainless steel membrane flashing. **BOND-N-FLASH** mastic may be applied to concrete, brick, stone, metal, wood, PVC and most plastics and painted surfaces.

Uses: Used primarily as a secondary seal on horizontal and vertical seams, overlaps, punctures, other terminations such as end dams or protrusions.

Features:

- Excellent resistance to weathering, shrinking and cracking
- Excellent strength and flexibility
- Resistant to U.V. degradation
- Withstands a wide range of high heat and extreme cold from -20 degrees F to 200 Degrees F
- Application temperatures are 0 Degrees F to 120 Degrees F
- Can be painted

Application: Apply **BOND-N-FLASH Mastic** on a surface that is dry, clean and free of dust. Do not solvent wipe substrate with either alcohol or oil-containing solvents. Mineral Spirits may be used. Surface should be dry before applying the **BOND-N-FLASH Mastic**. Apply the mastic either by trowel or caulking gun onto a dry surface. If applied with a caulking gun, strike the bead of with a trowel to about ¼” in thickness and ½” to 1 inch in width.

On the bottom edge of vertical applications, **BOND-N-FLASH Mastic** should be troweled upward. **BOND-N-FLASH Mastic** should be used liberally around protrusions, laps and other areas requiring patch pieces.

Coverage: The amount of **BOND-N-FLASH Mastic** will vary widely from job to job. One gallon of **BOND-N-FLASH Mastic** one (1) inches wide by one-quarter (1/4) inch thick will yield approximately 100 lineal feet of coverage.

Packaging:

Available in five (5) gallon pails 50 lbs/pail
Available in 30 oz. cartridge (12/box); 16 lbs./box

Storage: If stored in original unopened container at or below 90 degrees F, shelf life is 12 months from date of shipment. Average storage temperatures opened 65 – 110 degrees F. Do not store in direct sunlight.

Safety: Use with adequate ventilation. Inhalation of vapors may cause slight eye or throat irritation. See MSDS for additional information